

Customer: **Guizhou Haotian Optoelectronics Tech.**

P.O.#

Date: 6-Sep-15

Job #

H0FSD383

Customer ID: **AI203**

Sample ID:

H150906003

No ID.

[Rev: 2015-09-09 09:40:24]

Element	Concentration [ppm wt]	Element	Concentration [ppm wt]
Li	-	Pd	-
Be	-	Ag	-
B	< 0.05	Cd	-
C	-	In	-
N	-	Sn	-
O	Matrix	Sb	-
F	-	Te	-
Na	< 0.1	I	-
Mg	< 0.1	Cs	-
Al	Matrix	Ba	-
Si	< 0.1	La	-
P	< 0.1	Ce	-
S	< 0.5	Pr	-
Cl	< 0.1	Nd	-
K	< 0.5	Sm	-
Ca	< 0.5	Eu	-
Sc	-	Gd	-
Ti	< 0.05	Tb	-
V	< 0.05	Dy	-
Cr	< 0.5	Ho	-
Mn	< 0.05	Er	-
Fe	< 1	Tm	-
Co	-	Yb	-
Ni	< 0.5	Lu	-
Cu	< 1	Hf	< 0.1
Zn	< 0.5	Ta	Electrode
Ga	< 0.1	W	< 20
Ge	-	Re	< 0.05
As	-	Os	-
Se	-	Ir	-
Br	-	Pt	-
Rb	-	Au	-
Sr	-	Hg	-
Y	-	Tl	-
Zr	< 0.1	Pb	< 0.1
Nb	< 0.5	Bi	-
Mo	< 0.5	Th	-
Ru	-	U	-
Rh	-		

A.GUI (Analyst)



ISO 17025



Testing Cert. #2797.04

Page 1 of 1 - GDMS

Analyzed according to WI F rev. 12/06/12

Reviewed by _____

Precision and bias typical of GDMS measurements are discussed under ASTM F1593.
This shall not be reproduced except in full without written approval of the laboratory.